

ProRox® SL 560

ProRox SL 560 is a highly compression resistant stone wool slab for thermal and acoustic insulation of constructions where high temperatures and mechanical loads (e.g. vibrations) occur.



Product properties

Properties	Performance												Norms
Thermal conductivity	T_m (°C)	50	100	150	200	250	300	350	400	500	600	700	EN 12667
	λ (W/mK)	0,042	0,047	0,052	0,057	0,064	0,072	0,082	0,093	0,117	0,147	0,181	
Maximum Service Temperature	700°C (1292°F)												EN 14706
	750°C (1382°F)												ASTM C411
Reaction to fire	Euroclass A1												EN 13501-1
	Surface burning characteristics; Flame spread=passed, Smoke development=Passed												ASTM E84 (UL 723)
Nominal density	175 kg/m ³ (10,9 lb/ft ³)												EN 1602
Water Absorption	< 1 kg/m ²												EN13468
	Water vapour absorption (Vapor sorption) \pm 0,02%vol												ASTM C1104/C1104M
Water vapour diffusion resistance	$\mu = 1$												EN 14303
Compression resistance	> 30 kPa (at 10% deformation)												EN 826
Designation code	MW EN 14303-T4(T3 if $t < 40$)-ST(+)-700-CS(10)30(if $t \geq 50$)-WS1												EN 14303

Compliance

ProRox SL 560 Slabs comply with the requirements as set by EN14303, CINI 2.2.01 and ASTM C612: type IA, IB, II, III, IVA.

As ROCKWOOL has no control over insulation design and workmanship, accessory materials or applications conditions, ROCKWOOL does not warranty the performance or result of any installation containing ROCKWOOL products. ROCKWOOL's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose. ROCKWOOL Technical Insulation reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.

ROCKWOOL® Technical Insulation, ROCKWOOL®, SeaRox® and ProRox® are registered trademarks of ROCKWOOL International A/S and cannot be used without a prior written consent.